

BORE-GROUT™

Horizontal Grout

Description	BORE-GROUT [™] horizontal heat loop grout is a bentonite material designed for use in grouting boreholes containing horizontally installed ground source heat loops. BORE-GROUT horizontal heat loop grout is also used where a grout is required to be placed around a horizontally installed product line. BORE-GROUT horizontal heat loop grout is designed to be mixed and pumped neat with standard horizontal directional drilling (HDD) rig equipment. Alternately, silica sand may be added to BORE-GROUT horizontal bentonite grout to increase the thermal conductivity, up to 1.2 BTU/hr·ft. ^o F (0.69 – 2.08 watts/m·°C). Sand-enhanced BORE-GROUT horizontal heat loop grout systems will require dedicated grouting equipment for mixing and placement. BORE-GROUT horizontal heat loop grout should only be used in the saturated zone.					
Applications/	The use of BORE-GROUT horizontal heat loop grout promotes the following:					
Functions	 A thermally conductive grout medium with low permeability for sealing ground source heat loops installed in horizontal bores 					
	A low permeability bentonite grout for sealing horizontal bores					
Advantages	Promotes efficient heat transfer					
U	 Produces a uniform slurry for smooth pumping - No need to add extra water 					
	Creates a low permeability seal					
	Develops a permanent, flexible seal to prevent commingling between aquifers					
	No heat of hydration					
	No Portland or aluminum cement added					
	No gypsum added					
	NSF/ANSI Standard 60 Certified					
Typical	Appearance	Beige to tan powder				
Properties	Specific gravity	2.6				
ropences	Thermal Conductivity (k)	0.4 BTU/hr⋅ft⋅º , neat				
		0.69 watts/m⋅°C , neat				
	 Yield Volume (before pumping) 	22.3 gal/batch				
		84.4 liters/batch				
	Grout Weight (before pumping)	9.7 lb/gal				
	Typical Darmaphility*	1.17 SG 3.0 x 10 ⁻⁸ cm/sec				
	Typical Permeability*	*Test data can be provided upon request.				
Recommended		one 50-lb (23 kg) bag of BORE-GROUT™				
Treatment	horizontal heat loop grout in 20 gallon	s (15.1 liters) of water.				

• Please refer to the treatment tables below for slurry properties.

Because the conditions of use of this product are beyond the seller's control, the product is sold without warranty either express or implied and upon condition that purchaser make its own test to determine the suitability for purchaser's application. Purchaser assumes all risk of use and handling of this product. This product will be replaced if defective in manufacture or packaging or if damaged. Except for such replacement, seller is not liable for any damages caused by this product or its use. The statements and recommendations made herein are believed to be accurate. No guarantee of their accuracy is made, however.

Recommended

Treatment Tables

k Btu/hr·ft·	Silica Sand F (lb/50 lb bag)	Water (gal/50 lb bag)	Slurry Volume Yield (gallons)	Density (Ib/gal)	Total Solids
0.4	0	20.0	22.3	9.7	23.0%

k watts/m⋅°C	Silica Sand (kg/23 kg bag)	Water (liters/23 kg bag)	Slurry Volume Yield (liters)	Specific Gravity	Total Solids
0.69	0	75.7	84.4	1.17	23.0%

Recommended Mixing Procedure

- Pre-treat mixing water with Soda Ash (sodium carbonate) to reduce total hardness to less than 100 mg/l and raise pH to 8.5-9.5.
- Using the HDD rig equipment, blend one 50-lb bag of BORE-GROUT horizontal heat loop grout into 20 gallons (75.5 liters) of fresh water. Rate of addition should be about 20 seconds per 50-lb (23 kg) bag. Mix adequately, typically 30 seconds, depending on the mixer.
- Blend, do not over mix. Pump without delay through drill rods while pulling product line

NOTE: Bentonite grouts may not be appropriate for formation water chemistries where total hardness is 500 parts per million or greater and/or the chloride content is 1500 parts per million or greater. If questions regarding subsurface environments arise, it is always best to consult your local Baroid IDP representative to determine if the Baroid product of choice is appropriate for the given conditions.

Alternate Treatment • Do

t
 • Do not use a centrifugal pump

Technical Service

- Using a standard grouter or other mixing device, , blend one 50-lb (23 kg) bag of BORE-GROUT horizontal heat loop grout into water. Rate of addition should be about 10 to 20 seconds per 50-lb bag.
- Immediately add sand at a rate of 5 to 10 seconds per 50 pounds (23 kg) and pump. Additional mixing time after the addition of sand is not required and is not recommended.
- Dry sand ranging between 50 and 70 mesh and containing greater than 99% silica is recommended.
- Blend, do not over mix. Place through a 1.25 inch (32 mm) minimum I.D. tremie into

Packaging BORE-GROUT horizontal bentonite grout is packaged in 50-lb (23 kg) multiwall paper bags, containing 0.7 ft³ (0.02 m³). 3000-lb supersacks are available by special order. Availability BORE-GROUT horizontal bentonite grout can be purchased through any Baroid Industrial

allability BORE-GROUT horizontal bentonite grout can be purchased through any Baroid Industrial Drilling Products Retailer. To locate the Baroid IDP retailer nearest you contact the Customer Service Department in Houston or your area IDP Sales Representative.

Baroid Industrial Drilling ProductsProduct Service Line, Halliburton3000 N. Sam Houston Pkwy E.Houston, TX 77032Customer Service(800) 735-6075 Toll Free

(877) 379-7412 Toll Free

Because the conditions of use of this product are beyond the seller's control, the product is sold without warranty either express or implied and upon condition that purchaser make its own test to determine the suitability for purchaser's application. Purchaser assumes all risk of use and handling of this product. This product will be replaced if defective in manufacture or packaging or if damaged. Except for such replacement, seller is not liable for any damages caused by this product or its use. The statements and recommendations made herein are believed to be accurate. No guarantee of their accuracy is made, however.

(281) 871-4612

(281) 871-4613