



EZ-MUD[®] DP GOLD

Borehole Stabilizing Dry Polymer

Description

EZ-MUD[®] DP GOLD borehole stabilizing dry synthetic polymer contains high molecular weight partially hydrolyzed polyacrylamide/polyacrylate (PHPA) copolymer. EZ-MUD DP GOLD water-soluble polymer, when mixed with fresh water, hydrates quickly and forms a clear, viscous fluid. EZ-MUD DP GOLD dry polymer provides excellent borehole stability through a coating mechanism (encapsulation).

Applications/Functions

The use of EZ-MUD DP GOLD dry polymer assists and promotes the following:

- Stabilize reactive clay and shale formations
- Keep trench excavation open during the construction
- Produce high viscosity solids-free slurry
- Enhance rheological properties of a low-solids drilling mud
- Enhance core recovery in continuous wireline coring operations
- Flocculate non-reactive solids in reserve pit at low concentrations
- Reduce torque and drag

Advantages

- Disperses and mixes easily with minimal shear
- Improved product performance due to enhanced solubility of product mixed
- Enhanced product utilization due to reduction in amounts of un-yielded product produced during mixing
- Helps impart high degree of lubricity
- Compatible with other drilling fluid additives when added in proper sequence
- Non-fermenting
- No petroleum distillates involved
- Breaks down chemically with bleach (sodium hypochlorite)
- NSF/ANSI Standard 60 Certified

Typical Properties

Appearance	Yellow, free-flowing granules
pH (0.15% solution)	7.5
Density	1.45 (as packaged)

Recommended Treatment

Approximate Amounts of EZ-MUD DP GOLD Added to Drilling Fluid System

Drilling Application/Desired Property	lbs/100 gal	lbs/bbl	kg/m ³
<i>Added to fresh water (To formulate a clay-free drilling fluid)</i>			
• To help stabilize water-sensitive formations	0.5 - 2.0	0.2 - 0.8	0.6 - 2.4

• To help stop rod vibration, reduce torque and pumping pressure	0.5 - 1.5	0.2 - 0.6	0.6 - 1.8
Added to QUIK-GEL® or BORE-GEL® Drilling Fluids			
• To help retard reactive shale and clay and enhance lubricity	0.25 - 0.75	0.1 - 0.3	0.3 - 1.0
Added to injection liquid in air/foam drilling applications			
• To help improve foam performance and hole conditions	0.5 - 1.0	0.2 - 0.4	0.6 - 1.2

Notes:

- Make-up water used to mix EZ-MUD DP GOLD polymer, viscosifier or additive should meet the following quality:
total chloride less than 1500 ppm (mg/L)
total hardness less than 150 ppm as calcium
total chlorine less than 50 ppm
water pH between 8.5-9.5
- Reduce total hardness of make-up water by adding soda ash (sodium carbonate) at 0.5 to 1 pound per 100 gallons (0.6 - 1.2 kg/m³) of make-up water.
- EZ MUD DP polymer, viscosifier or additive can be chemically broken down with regular household liquid bleach (5% sodium hypochlorite). Use one gallon of liquid bleach per 100 gallons (10 liters/m³) of fluid formulated with EZ MUD DP polymer, viscosifier or additive. Do not use perfumed liquid bleach or solid calcium hypochlorite.

Packaging

- EZ-MUD DP GOLD polymer, viscosifier or additive is packaged in 14-lb (6.35-kg) resealable plastic containers.

Availability

EZ-MUD DP GOLD dry polymer can be purchased through any Baroid Industrial Drilling Products Retailer. To locate the Baroid IDP retailer nearest you contact the Customer Service Department in Houston or your area IDP Sales Representative.

Baroid Industrial Drilling Products

Product Service Line, Halliburton

3000 N. Sam Houston Pkwy E.

Houston, TX 77032

Customer Service	(800) 735-6075 Toll Free	(281) 871-4612
Technical Service	(877) 379-7412 Toll Free	(281) 871-4613