



MAX-YIELD™ HP

Low Solids Geothermal Grout

Description MAX-YIELD™ HP, low solids geothermal grout, is a bentonite based grout designed for use in the grouting of boreholes containing ground source heat loops, and related applications. MAX-YIELD HP low solids geothermal grout is designed to be combined with MAX-YIELD™ TCM, thermally conductive media, at various water concentrations to yield a grout with a resultant thermal conductivity ranging from 1.0 to 1.2 BTU/ft· hr·°F (1.73 – 2.08 watts/m·°C)

Applications/Functions

- MAX-YIELD HP, low solids geothermal grout, provides a stable grout with low permeability and an effective medium for incorporation and suspension of thermally conductive material to enhance subsurface heat transfer of ground source heat loops.

Advantages

- Uses approximately half the amount of grout than traditional applications
- Reduced on-site material footprint and handling requirements
- Helps minimize overall logistics and operational costs
- Meets and exceeds industry standard for hydraulic conductivity of $< 1 \times 10^{-7}$ cm/sec
- Produces a uniform slurry for smooth and efficient pumping

Typical Properties

- Appearance: Grey to tan powder
- Specific Gravity: 2.6
- Permeability: $< 1.0 \times 10^{-7}$ cm/sec

Recommended Treatment The recommended treatment is based on the desired thermal conductivity or k value. Please refer to treatment table below.

k BTU/hr·ft·°F	MAX-YIELD HP Low Solids Geothermal Grout (# of 50-lb sacks)	MAX-YIELD TCM Thermally Conductive Media (# of 36-lb sacks)	Water (US gal)	Slurry Volume Yield (US gal)	Total Solids (by weight)
1.0	1	1	38.5	42.7	21.1%
1.2	1	1	36.0	40.2	22.3%

Packaging MAX-YIELD HP, low solids geothermal grout, is packaged in 50-lb (22.7-kg) multiwall paper bags.

Additional Information

- The grouting material and method selected will depend upon the specific subsurface environment including all prevailing geological and hydrological factors and any existing regulatory requirements. The grouting process may not be complete until the grout is static at the desired level.
- The use of a bentonite-based solution may not be appropriate in unsaturated geologic conditions or environments where the formation water chemistry has a total hardness greater than 500 parts per million and/or a chloride content of greater than 1500 parts per million.
- If questions arise regarding subsurface environments it is always best to consult your local Baroid IDP representative to determine if the Baroid product of choice is appropriate for the given conditions

Availability MAX-YIELD HP, low solids geothermal grout, can only be purchased through Baroid Industrial Drilling Products Retailers. To locate the Baroid IDP retailer nearest you contact the Customer Service Department in Houston or your area IDP Sales Representative.

**Baroid Industrial Drilling Products
Product Service Line, Halliburton**
3000 N. Sam Houston Pkwy. E.
Houston, TX 77032

Customer Service (800) 735-6075 Toll Free (281) 871-4612
Technical Service (877) 379-7412 Toll Free (281) 871-4613